Lifting Solutions Group
Axel Johnson International

# Polypropylene Fibre Rope 3-Strand Staplespun

## Product information



General purpose rope for a variety of marine applications; mooring, towing, fishing, pick-up lines, lifting slings, general purpose use.

**Design:** Spliced fibre.

**Specific gravity:** 0,91 (floats)
**Melting point:** Approx. 165°C
**Elongation:** Approx. 30%.
**Strength wet/dry:** 100%
**Shock Absorption:** Very Good
**Water Absorption:** None
**Abrasion Resistance:** Good
**Standard:** EN ISO 1346:2004

... *Read more*

**Material:** Polypropylene, resistant to rot, most acids and alkalies. The fibre is UV-stabilized against sunlight.
**Finish:** White

**Traction Levage**
marketingtl@traclev.com

© November 2026 - All Rights Reserved

Lifting Solutions Group
Axel Johnson International

# Polypropylene Fibre Rope 3-Strand Staplespun

## Technical data

| Part code | Diameter mm | Minimum Strength Kgf | Weight kg/100m |
|---|---|---|---|
| 300300600000120 | 6 | 600 | 1.7 |
| 300300800000120 | 8 | 1,060 | 3 |
| 300301000000120 | 10 | 1,560 | 4.5 |
| 300301200000120 | 12 | 2,210 | 6.5 |
| 300301400000120 | 14 | 3,050 | 9 |
| 300301600000120 | 16 | 3,770 | 11.5 |
| 300301800000120 | 18 | 4,810 | 14.8 |
| 300302000000120 | 20 | 5,800 | 18 |
| 300302200000120 | 22 | 6,950 | 22 |
| 300302400000120 | 24 | 8,130 | 26 |
| 300302800000120 | 28 | 10,710 | 35.5 |
| 300303200000120 | 32 | 13,460 | 46 |
| 300303600000120 | 36 | 16,930 | 58.5 |
| 300304000000120 | 40 | 20,500 | 72 |
| 300304400000120 | 44 | 24,570 | 88 |
| 300304800000120 | 48 | 28,550 | 104 |
| 300305200000120 | 52 | 33,040 | 122 |
| 300305600000120 | 56 | 37,830 | 142 |
| 300306000000120 | 60 | 43,240 | 163 |
| 300306400000120 | 64 | 48,950 | 185 |
| 300307200000120 | 72 | 61,490 | 234 |
| 300308000000120 | 80 | 75,560 | 290 |

**Traction Levage**
marketingtl@traclev.com
© November 2026 - All Rights Reserved