



DURAhoist 24C

Product information



- Rotation-resistance properties to use without swivel
- 12-strand compacted rope, lubricated during stranding and closing
- High resistance to crushing and abrasion
- Achieves very good bending fatigue results and good flexibility
- High breaking load resistance

[... Read more](#)

Rope construction: 24x7, Warrington steel core

Marking: According to standard

Standard: EN 12385-4

RCN: 23-1

Tolerance Ø: +1% to +4%

Luffing crane



Self-erected crane



Tower crane



DURAhoist 24C

Technical data

Part code	Rope diameter	Tensile strength N/mm ²	Finish	Rope lay	Min. breaking force kN	Steel area mm ²	Lubrication	Weight kg/100m
104100726270249	7.2	1,960	Galvanized	zZ	42	29	SupplierStandard	22
104100806270249	8	1,960	Galvanized	zZ	56	35.8	SupplierStandard	28
104100906270249	9	1,960	Galvanized	zZ	71	45.4	SupplierStandard	36
104101006270249	10	1,960	Galvanized	zZ	88	56	SupplierStandard	46
104101106270249	11	1,960	Galvanized	zZ	107	67.8	SupplierStandard	56
104101206270249	12	1,960	Galvanized	zZ	127	80.6	SupplierStandard	67
104101306270249	13	1,960	Galvanized	zZ	149	94.6	SupplierStandard	78
104101406270249	14	1,960	Galvanized	zZ	175	109.8	SupplierStandard	91
104101606270249	16	1,960	Galvanized	zZ	226	143.4	SupplierStandard	120
104101806270249	18	1,960	Galvanized	zZ	286	181.4	SupplierStandard	148
104102006270249	20	1,960	Galvanized	zZ	353	224	SupplierStandard	188